



AIR FILTER TESTING LABORATORIES, INC.

4632 Old LaGrange Road • Crestwood, Kentucky 40014

ASHRAE AIR FILTER TEST STANDARD 52-76
STATICALLY TESTED DEVICES

DEVICE TESTED

TEST REQUESTED BY CUMULUS FIBRES, INC.
MANUFACTURER CUMULUS FIBRES, INC.
PRODUCT NAME MEDIA PAD

REPORT NO. 6601
TEST NO. 1
SHEET NO. 1

HOW LABORATORY PROCURED TEST SAMPLE FURNISHED BY MANUFACTURER
MODEL NO. 1008WOT22 DIMENSIONS 24 in. H 24 in. W 1 in. D

RATED PERFORMANCE DATA FROM MANUFACTURERS CATALOG NO.	DATED	
AIR FLOW CAPACITY		
INITIAL RESISTANCE		
FINAL RESISTANCE		
INITIAL ATMOSPHERIC DUST SPOT EFFICIENCY		
AVERAGE ATMOSPHERIC DUST SPOT EFFICIENCY		
AVERAGE SYNTHETIC DUST WEIGHT ARRESTANCE		
ASHRAE DUST HOLDING CAPACITY		


TEST RESULTS

TEST AIR FLOW RATE	<u>1200 CFM</u>	<u>300</u>			
INITIAL RESISTANCE		<u>0.20</u>			<u>FPM</u>
FINAL RESISTANCE					<u>in. W.G.</u>
INITIAL ATMOSPHERIC DUST SPOT EFFICIENCY				<u>1.00</u>	<u>in. W.G.</u>
AVERAGE ATMOSPHERIC DUST SPOT EFFICIENCY				<u>20</u>	<u>%</u>
AVERAGE SYNTHETIC DUST WEIGHT ARRESTANCE				<u>92</u>	<u>%</u>
ASHRAE DUST HOLDING CAPACITY				<u>230</u>	<u>grm.</u>

TEST SECTION DUCT SIZE 24 in. x 24 in. DUST FEEDING RATE 2.0 gm/1000 CF
SEE BACK SIDE (PAGE 1A) FOR PERFORMANCE CURVES

PHYSICAL DESCRIPTION

FACE DIMENSIONS 24 in. x 24 in.
DEPTH 1 in. Nom.
MEDIA AREA 4 ft²
TYPE MEDIA NONWOVEN SYNTHETIC
TYPE & AMOUNT ADHESIVE TACKIFIED



DATE 4-22-1992 TEST SUPERVISOR J.P.S. ENGINEERING APPROVAL David S. Murphy Jr.